



Different materials used in lithium ion batteries (LIBs) and its combination with nanomaterials

Shishir kumar¹, Priyanka Singh¹, Vipin Kumar Singh², R B Singh³

¹Department of Chemistry, Maharishi University of Information Technology, Sitapur Road, IIM Bypass, Bhitauli Tiraha, Lucknow, Uttar Pradesh, India

²Department of Chemistry, Agra College, Agra, Uttar Pradesh, India

³Scientist, Professor, School of Life Sciences, Dr. Bhimrao Ambedkar University, Khandari Campus, Agra, Uttar Pradesh, India

Abstract

People's demand of energy has increased a lot not just high power but also convenience and security since the 2nd industrial revolution. Batteries have been popular among people of all ages since it was invented for it satisfied most of them. However, most of them can only be used once so that is the reason why lithium-ion rechargeable batteries are invented. Lithium-ion batteries (LIBs) hold well on their mass and volume, which solves the bulks obstacles over centuries. More importantly, they own wonderful voltage as well as capacity. With the development of lithium-ion batteries (LIBs), people's demand of better materials became more and more strong. Graphite material has had a dominant position in both commercial and industrial area. However, there are more extraordinary compounds whose properties like capacity and potential are better than those of carbon. Therefore, several new materials that scientists researched about are introduced below to compare them with carbon. Meanwhile, nanomaterials have caught people's eyes because they are newborn subject for science. By modification, they can improve properties of different materials. This article is a literature review of Lithium-ion batteries (LIBs). Moreover, it will combine batteries with nanomaterials together to explore better methods to use in Lithium-ion batteries (LIBs).



Keywords: Lithium-ion batteries, nanomaterials, anode, cathode, combination

Introduction

The traditional fuels like petrol that are often used always have a large amount of greenhouse gas emission, which do a large harm to the environment and global warming [1]. Therefore, the governments tried to solve the problems by changing the original bunkers into electric charges [2]. Lithium ion batteries (LIBs) have been trying to be created since the last two decades. Due to traditional batteries' low efficiency and limited energy, they could not satisfy the requirements of the power supply in the industrial fields [3]. After lithium batteries were invented, they later emerged in Japan for the use in cameras, laptops and cell phones, which first turned lithium-ion chemistry into commercial products. Compared to other sorts of charges, for instance Ni-Cd and Ni-MH, Lithium-ion batteries (LIBs) own better energy as well as density. However, it is impossible to put them into use especially in industrial applications due to the high power. Therefore, there's still a long way to go in order to spread Lithium ion Battery (LIB) across [4]. The word 'nano' has been used in many kinds of fields of knowledge and refers to the low weight and height of a person initially, which finally represents the material whose size is among 1-100nm materials. Based on in-common physical and chemical properties, they can be divided into five main categories [5]. With the development of nanomaterials, they have been applied to different fields as well as the batteries. For example, carbon nanomaterials are widely used, and they are famous for microscopy structure, which has low density, high intensity, extraordinary conductivity and flexibility [6]. The working principles of Lithium ion battery (LIB) are quite similar to traditional ones, and they have three main components: anode, cathode and electrolyte. The positive charge is where reduction reaction happens, and its component are often Lithium metal oxide while the negative charge is the opposite. We use carbon anode as an example

to describe the working function of Lithium - ion Batteries (LIBs) [7].

Charge reactions of carbon anode of Lithium -ion batteries (LIBs)



It is known to us all that Lithium ion battery (LIB) can be divided into three essential parts: anodes, cathodes and electrolyte. Therefore, this article will mainly talk about the anode and cathode materials that have been used in Lithium ion Batteries (LIBs) and it will be described in the order of the batteries parts.

Materials and Methods

Anode Materials: The anode is where oxidation reactions happen and they are the most important to measure whether a battery is effective enough, so they should not be active material such as metals. For this reason, lots of high-performance and novel materials are found and three stable anode materials: carbon, silicon and metal sulfide compounds are chosen to be discussed. Carbon and graphite are widely used because of their low cost as well as high ion conductivity. However, silicon has been regarded as one of the best alternatives because of their wonderful capacity in theory and perfect working voltage [8].

Graphene or Graphite material (Carbon nanomaterial):

Carbon nanomaterials are the foundation during the development of Lithium ion Battery (LIB) after they replaced the firstly used hard carbon. Graphite material has low de-lithiation potential and specific capacity of 372 mAh

g^{-1} (theory), as a consequence, it improves the density of Lithium ion batteries (LIBs) [9]. Carbon nanomaterials offer exceptional electrical conductivity and a large theoretical surface area. Meanwhile, because of the different sorts of nanomaterials, carbon nanomaterials have different categories as well, such as carbon nanotubes and graphene with a single layer of carbon atoms. Therefore, various morphologies lead to the flexibility of the batteries, which means they can be wearable in biology [10]. Carbon nanotubes can be fabricated into distinct dimensional microscopy structures owing to the ultrahigh length-to-diameter ratio. Moreover, graphene is one of the newest stuff among carbon materials. When used in anodes, graphene can facilitate rapid lithium-ion diffusion, leading to improved rate performance. It seems that there are still shortcomings for carbon nanomaterials to improve. For example, their cycle stability should be enhanced, and the production cost must be lower [11]. Even though carbon nanomaterials may not be the best choice for Lithium ion batteries (LIBs), they still occupy the majority position of the market share, which shows the fact that they keep well balance between their costs and their properties. It claimed that they found reversible super dense ordering of graphene layers with over -372 mAh/g potential [12]. The research showed that the graphite intercalation compounds (GICs) can increase the ability for Lithium storage [13]. Moreover, that the specific electrolytes could provide plating Lithium thus leading to higher Lithium ion batteries (LIBs) density. As a matter of fact, these reports are not enough, there is still a long way to go for carbon nanomaterials [14].

Silicon and Silicon Oxide Nanoparticles: Silicon has been treated as next-generation Lithium ion battery (LIB) anode for it has a much higher capacity than graphite especially in the gravimetric capacity potential field. It has $4200 \text{ mAh}\cdot\text{g}^{-1}$ in theory, more than 11 times that of graphite of $372 \text{ mAh}\cdot\text{g}^{-1}$. Silicon (Si) is the second most abundant element in soil and more eco-friendly, which makes it an attractive alternative for anode material [15]. Scientists proved that silicon (Si) is better than graphite because it can definitely shorten the transmission distance of Lithium ions, thus raising the capacity of nanostructured anodes. They recognized that though graphite ones have better electrical conductivity than silicon, they offer much more safety issues due to higher voltage. Silicon's potential is much lower when operating. However, it cannot be applied to practical use for following reasons. Firstly, while being alloyed and dealloyed with ions, the crystal structure of the silicon will be destroyed. Consequently, voltage will change and be unstable. However, the silicon's large volume expansion upon lithium insertion is around 360% for $\text{Li}_{1.4}\text{Si}$ that leads to poor cyclability. To alleviate the problem, we can try to nanosizing silicon by reducing the mechanical stress and altering strategies to enhance the electrode's structural integrity [16].

Metal and metal oxides: Metal and metal oxides, such as Lithium itself and tin oxide (SnO_2), have been explored for their high theoretical capacities. Graphite anodes are on their bottlenecks for they are heavy and have limited densities. As for Lithium ion batteries (LIBs), theoretical specific capacities are the higher, the better while negative electrochemical potentials are the opposite. Therefore, Lithium itself can definitely be taken into consideration as it

has capacities of 3860 mAh g^{-1} and 2061 mAh cm^{-3} and -3.04 V negative potential compared to hydrogen electrodes [17]. Metal oxide anodes have been regarded as another choice to take the place of carbon anodes because they are not poisonous and with special properties. Take iron as an example, it naturally has two common oxides: Fe_2O_3 and Fe_3O_4 . It showed that the transition formula: $\text{Fe}_2\text{O}_3 + 6\text{Li}^+ + 6\text{e}^- \rightleftharpoons 2\text{Fe} + 3\text{Li}_2\text{O}$ owns 1006 mAh g^{-1} in theory [18] also several times of carbon. Moreover, Fe_2O_3 's expansion voltage is range to $0.005\text{--}3.0 \text{ V}$, much smaller than both silicon and graphite. Fe_3O_4 has raised the people's interest since decades ago. It has extraordinary capacity as well ($\approx 926 \text{ mAhg}^{-1}$). However, they both have drawbacks which have not been solved. Because of oxygen's physical properties and its limited weight, while the metal is covered by its small thickness the whole battery will stop reacting gradually and Lithium ion batteries (LIBs) efficiency will be decreased consequently. More importantly, lithium is one of the most active metals among all the elements, so it is quite hard to control the reaction speed, and the techniques are still immature. Besides, it is known to all that transition metal oxides and sulfides have poor electrical conductivity compared to metals. One practical method is to nanostructure these materials can improve their electrochemical performance by increasing the active surface area and reducing the diffusion length for lithium ions.

Cathode Materials: The cathode material is crucial for the battery's energy density and voltage and it accounts for more than 40% in rechargeable Lithium ion batteries (LIBs). Interestingly and their efforts for the development of Lithium ion batteries (LIBs). Using nanomaterials in the cathode can improve the battery's overall performance by enhancing the redox reaction kinetics.

Layered structures LiCoO_2 : The LiCoO_2 has been applied to commercial usage long time ago, which is the earliest among all cathodes. Its crystal structure ensures the stability of the cations and Lithium ions with octahedral structures and six oxygen atoms closely around them. Its theoretical capacity is as high as 274 mAh g^{-1} . Nevertheless, though LiCoO_2 has a high capacity in theory, it can only release more than half of it during the reaction (140 mAh g^{-1}). That is because when the charge voltage reaches to 4.2 V , the amount of lithium ion will decrease and be released, leading to Lithium ion batteries (LIBs) low efficiency [19]. For LiCoO_2 seems to be an ideal cathode material, scientists made plenty of efforts in order to cope with lithium ions lost. One doable way is to LiCoO_2 surface modification with carbon. It can keep the cathode away from the electrolyte and prevent the decomposition of lithium.

Lithium Manganese Oxides (LiMn_2O_4): Spinel-structured Lithium Manganese Oxides are known for their thermal stability and safety profile. It was brought forward and had application in both academic and industrial filed. It is popular among people by several reasons: Firstly, it has a specific three-dimensional structure which equally contains Mn^{2+} and Mn^{3+} . Secondly, the capacity is around 148 mAh g^{-1} lower than both theoretical and discharge ones of LiCoO_2 . Although it has many advantages, there still exists some problems. Both LiMn_2O_4 and LiCoO_2 have phase

transitions during battery reactions, and they have capacity loss especially under high temperature. What's more, short cyclable life is another difficulty to conquer. The happening reason can be concluded as follows: Corrosion effect from electrolyte and dissolution of Manganese (Mn). During this period, the structure will change which contribute to particle collapse collide with each other then reduce the conductivity.

Lithium Iron Phosphate (LiFePO₄): The research about lithium iron phosphate came much later than the other materials [20]. However, compared to other traditional cathodes which are mentioned above, it is more promising with its 170 mAhg⁻¹ perfect capacity even at room temperature and longer cyclable life [21]. Meanwhile, with an olivine structure, LiFePO₄ offers a stable platform for lithium ions. Consequently, it seems one of the best to match the mechanisms of the Lithium ion batteries (LIBs) while using as the cathode. Nevertheless, it has lower electricity conductivity. Researchers have been trying to figure it out by modification. Several sorts of these methods have been included and take surface modification as an example. The definition of this noun phrase is to change the material on the surface and carbon coat is one of the most famous. After covering, it appears great electrochemical properties but prevents lithium ions' transition, so it is hard to say whether the efficiency has been improved or not. Fortunately, reduced metal oxides (RGO) came out. By its porous structure, lithium ions will have faster diffusion. Some scientists have tried to mix these two cathode materials together and studies have been done on this considerable theory [21].

Lithium Rich Layered Metal Oxides (LRLOs): The name of this kind of cathode is quite similar to the three examples above and that is because the only distinction of them is their structure. Unlike traditional ones which rely on redox action that transmits metal ions, its mechanism includes oxygen and redox actions both. However, it can accelerate Lithium ion batteries (LIBs) corrosion thus reducing the life span of the batteries. High-voltage cathode materials like lithium nickel manganese cobalt oxide (NMC) and lithium nickel cobalt aluminum oxide (NCA) faced the same situation of voltage decay. When comes to this case, nanostructure can have a huge impact. LRLOs can benefit a lot while reacting in a crystal structure [22].

Nanostructured Electrodes: Apart from choosing electrode materials, it is recommended that make some changes based on those materials. In recent years, nanostructures have raised people's interest and attracted more research. Nanostructure can be defined by different scale sizes: one, two or three dimensions which ranges from 1-100 nm. Beyond individual nanomaterials, the design of nanostructured electrodes is critical for maximizing the densities of nanomaterials. Moreover, security and cost should also be taken into consideration. Techniques such as nanocomposites, where nanomaterials are combined with conductive agents and binders, can create a synergistic effect that further improves battery performance.

Surface structures: Surface structures mean fibrining materials into different nanostructures. As we all know, nanomaterials own large surface-to-volume ratio, which can

increase the active material's exposure to the electrolyte then accelerate the reaction process and reduce the impact of side reactions. Moreover, there are ligands that can be attached to the surface. Those connections are important components to improve Lithium ion batteries (LIBs) properties [23]. In this part, three commonly used example will be discussed in detail.

Composite Structures: Composite structures mean combining different nanomaterials together then leverage their individual strengths. For example, a silicon nanoparticle anode can be combined with graphene to enhance conductivity and mechanical stability. Nanosizing can increase the tap density and improve the structural stability during charge-discharge cycles.

Porous Nanostructures: Porous nanostructures are another method to make more material explore to the electrolytes thus reducing the consumption of raw materials.

Conclusion

Porous nanomaterials can provide additional benefits, such as increased electrolyte accessibility and reduced diffusion path lengths for lithium ions, leading to improved rate performance and capacity. The integration of nanomaterials in the anode and cathode of lithium-ion batteries offers a Pathway to overcome current limitations and achieve the next generation of high-performance energy storage systems. Continued research into material synthesis, nanostructure design, and understanding of lithium-ion transport mechanisms will be pivotal in realizing the full potential of nanomaterials in Lithium Ion Batteries (LIBs). This paper has provided an overview of the role of nanomaterials in enhancing the performance of anodes and cathodes in Lithium-ion batteries (LIBs). The unique properties of nanomaterials, when harnessed effectively, can lead to significant improvements in energy density, power density, cycle life and safety of Lithium ion batteries (LIBs). As research progresses, the development of novel nanomaterials and their strategic integration into battery architectures will continue to push the boundaries of energy storage technology.

References

1. Huang RJ. *Nature*,2014;514:218–222.
2. Geels FW. *Energy Res Soc Sci*,2018;37:224–231.
3. Niu H. *J Energy Storage*,2024;88:111666-111672.
4. Chen W, Liang J, Yang Z, Li G. *Energy Procedia*,2022;158:4363–4368.
5. Mekuye B, Abera B. *Nano Select*,2023;4(8):486–501.
6. Wu Z. *Advanced Materials*,2019;31(9):1800716-1800720.
7. Mart-Flores M, Cecilia A, Costa-Castelló R. *Energies*,2023;16(19):6846-6852.
8. Nzereogu PU, Omah AD, Ezema FI, Iwuoha EI, Nwanya AC. *Applied Surface Science Advances*,2022;9:100233-100238.
9. Li X, Zhang M, Yuan S, Lu C. *Chem Electro Chem*,2020;7(21):4289–4302.
10. Wu Z. *Adv Mater*,2019;31(9):2218-2224.
11. Padhi AK, Nanjundaswamy KS, Goodenough JB. *J. Electrochem. Soc.*,1997;144(4):1188–1194.
12. Guo YG, Hu JS, Wan LJ. *Advanced Materials*,2008;20(15):2878–2887.

13. Choi JW, Aurbach D. *Nature Reviews Materials*,2016;1(4):01–16.
14. Zhang H, Yang Y, Ren D, Wang L, He X. *Energy Storage Mater*,2021;36:147–170.
15. Zuo X, Zhu J, Müller-Buschbaum P, Cheng YJ. *Nano Energy*,2017;31:113–143.
16. Wilson AM, Zank G, Eguchi K, Xing W, Dahn JR. *J. Power Sources*,1997;68(2):195–200.
17. Wang R, Cui W, Chu F, Wu F. *Journal of Energy Chemistry*,2020;48:145–159.
18. Fang S, Bresser D, Passerini S. *Adv Energy Mater*,2020;10(1):1902485-1902489.
19. Ren J. *Carbon Neutralization*,2023;2(3):339–377.
20. Naoi K, Iwamizu Y, Mori M, Naruoka Y. *J Electrochem Soc*,1997;144(4):1185–1188.
21. Li L. *J. Electrochem.Soc.*,2017;164(9):A2138–A2150.
22. Jang HY. *Nature Communications*,2024;15(1):01–11.
23. Boles MA, Ling D, Hyeon T, Talapin DV. *Nature Materials*,2016;15(2):141–153.